

v2-10-0 (AUDINER AU LEUR PET

JC18 Rec'd PCT/PTO 0 6 DEC 2001

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE ATTORNEY'S DOCKET NUMBER 3142 2.2 8 FORM PTO-1390 (REV 10-95)

			O THE UNITED STATES							
		DESIGNATED/ELECTEI CONCERNING A FILING		U.S. APPLICATION NO (1f known, see 37 CFR 1.5) 10/009674						
INT	ERN.	ATIONAL APPLICATION NO. PCT/US00/40156	INTERNATIONAL FILING DATE 8 June 2000	PRIORITY DATE CLAIMED 8 June 1999						
TIT	ITLE OF INVENTION LASER ABLATION OF DOPED FLUOROCARBON MATERIALS AND APPLICATIONS THEREOF									
APP	PPLICANT(S) FOR DO/EO/US									
	Michael McNeely and Arnold Oliphant									
Appl	licant	herewith submits to the United State	s Designated/Elected Office (DO/EO/US) the	e following items and other information:						
1.	X	This is a FIRST submission of items	s concerning a filing under 35 U.S.C 371.							
2.		This is a SECOND or SUBSEQUE	NT submission of items concerning a filing u	nder 35 U.S.C. 371.						
3.		This express request to begin national until the expiration of the applicable	al examination procedures (35 U.S.C. 371(f)) time limit set in 35 U.S.C. 371(b) and PCT A	at any time rather than delay examination Articles 22 and 39(1).						
4.		A proper Demand for International F date.	Preliminary Examination was made by the 19 th	h month from the earliest claimed priority						
5.	X	A copy of the International Applicat	ion as filed (35 U S C 371(c)(2))							
		a us transmitted herewith (req	uired only if not transmitted by the Internatio	nal Bureau)						
		b has been transmitted by the	International Bureau							
		c. 🗷 is not required, as the applic	cation was filed in the United States Receivin	g office (RO/US).						
6.		A translation of the International Ap	plication into English (35 U.S.C. 371 (c)(2))							
7.		Amendments to the claims of the Int	ernational Application under PCT Article 19	(35 U.S.C 371(c)(3))						
		a. are transmitted herewith (re	quired only if not transmitted by the Internati	onal Burcau)						
		b. have been transmitted by th	e International Bureau.							
		c have not been made; however	ver, the time limit for making such amendmen	ts has NOT expired.						
		d. have not been made and wil	Il not be made.							
8.		A translation of the amendments to t	the claims under PCT Árticle 19 (35 U.S C. 3	71(c)(3)).						
9.	X	An oath or declaration of the inventor	or(s) (35 U S.C. 371(c)(4)).							
10.		A translation of the annexes to the ln (35 U.S.C. 371(c)(5)).	nternational Preliminary Examination Report	under PCT Article 36						
Iten	ıs 11.	to 16. below concern document(s) (or information included:							
11.		An Information Disclosure Statemer								
12.	$\overline{\mathbf{x}}$		ing. A separate cover sheet in compliance wi	th 37 CFR 3 28 and 3.31 is included.						
13.	$\overline{\mathbf{x}}$	A FIRST preliminary amendment								
		A SECOND or SUBSEQUENT prel	ıminary amendment.							
14.		A substitute specification.								
15.										
16.	x	Other items or information. Certifi	cate of Mailing							

U.S. APPLICATION NO (I	If known, see 37 CFR 1 5) 1 0 0 9 6 7 4	PPLICATION NO US00/40156	ATTORNEY	7'S DOCKET NUMBER 3142 2.2.8					
	ing fees are submitted			CALCULATIONS	6 (PTO USE ONLY				
	FEE (37 CFR 1.492(a)(1)			-					
	as been prepared by the EP			•					
	eliminary examination fee p	· ·							
international sear	preliminary examination for rch fee paid to USPTO (37								
search fee (37 Cl	onal preliminary examination FR 1.445(a)(2)) paid to US	SPTO	\$1040.00						
International pre satisfied provisio	liminary examination fee pa ons of PCT Article 33(2)-(4	4)	\$ 100.00						
		APPROPRIATE BASIC		\$710.00					
from the earliest claim	for furnishing the oath or d led priority date (37 CFR 1	leclaration later than 2 2 492(e)).	20 30 months	\$					
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE						
Total Claims	30	(above 20)	X \$ 18 00	\$180.00					
Independent Claims	5	(above 3)	X \$ 84.00	\$168.00					
MULTIPLE DEPEND	DENT CLAIM(S) (if application		+ \$280.00	\$					
		TOTAL OF ABOVE CA	ALCULATIONS =	\$1058.00					
Reduction of ½ for file	ing by small entity, if applic	zable		\$					
2 20100			SUBTOTAL =	\$529.00					
Processing tee of \$130 from the earliest claims	0.00 for furnishing the Engled priority date (37 CFR 1.	.492(f)).	+						
= 2			NATIONAL FEE =	\$	ļ				
ree for recording the eaccompanied by an app	enclosed assignment (37 CF propriate cover sheet (37 CF	CFR 3 28, 3 31) \$40.00 p	per property +	\$40.00					
		TOTAL FE	EES ENCLOSED =	\$569.00					
				Amount to be refunded:					
<u> </u>				charged	\$				
	eredit card payment form for ase charge my Deposit Acce				the above foog. A				
dup	olicate copy of this sheet is	enclosed.	the amount of c		If the above ices. 71				
c. X The	c. The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No 13-0763. A duplicate copy of this sheet is enclosed								
NOTE: Where an appor (b)) must be filed an	propriate time limit under nd granted to restore the a	r 37 CFR 1.494 or 1.495 application to pending	status.	- 1 1	(37 CFR 1.137(a)				
SEND ALL CORRESP	'ONDENCE TO:		SIGNATURE	2000					
MADSON & ME			Evan R. Witt						
15 West South Te	-		NAME						
Salt Lake City, Ut									
United States of A			32,512						
Felephone: (801)	537-1700	N NUMBER	j						

U.S. APPLICATION NO (III $10/$	known, see 37 CFR 1.5) 0 0 9 6 7 4	ATTORNEY'S DOCKET NUMBER 3142 2.2.8								
17. X The following	ng fees are submitted:			CALCU	JLATIONS	(PTO USE ONLY				
BASIC NATIONAL	FEE (37 CFR 1.492(a)(1)	·(5):								
Search Report ha	s been prepared by the EP	O or JPO	\$ 890.00	1						
International prel	iminary examination fee p	}								
	preliminary examination for the fee paid to USPTO (37									
	onal preliminary examinati FR 1.445(a)(2)) paid to US									
	iminary examination fee p ns of PCT Article 33(2)-(4									
	ENTER .	APPROPRIATE BASI	C FEE AMOUNT =	\$710 0)					
	for furnishing the oath or ded priority date (37 CFR 1		20 30 months	\$						
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE							
Total Claims	30	(above 20)	X \$ 18.00	\$180.00)					
Independent Claims	5	(above 3)	X \$ 84.00	\$168.00)					
MULTIPLE DEPEND	ENT CLAIM(S) (if applic	able)	+ \$280.00	\$						
		TOTAL OF ABOVE C	ALCULATIONS =	\$1058.0	00					
Reduction of ½ for filing	ng by small entity, if appli	cable.		\$						
			SUBTOTAL =	\$529.00)					
	.00 for furnishing the Engled priority date (37 CFR 1		20 30 months +	\$						
		TOTAL	NATIONAL FEE =	\$						
	nclosed assignment (37 CI propriate cover sheet (37 C			\$40.00						
		TOTAL FE	ES ENCLOSED =	\$569.00)					
				An	nount to be refunded:	\$				
					charged	\$				
a. 🛛 A c	redit card payment form fo	or the amount of \$569.00) to cover the above f	ees is en	closed.					
	ase charge my Deposit Aco dicate copy of this sheet is		the amount of \$		to cove	r the above fees. A				
	c. The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 13-0763. A duplicate copy of this sheet is enclosed.									
	propriate time limit unde nd granted to restore the			- 1						
SEND ALL CORRESP	PONDENCE TO.		SIGNATURE	< U	M					
MADSON & ME	TCALF		Evan R. Witt							
15 West South Te			NAME							
Salt Lake City, U	-									
United States of A			32,512							
Telephone: (801)	537-1700		REGISTRATIO	N NUMI	BER					

Page 2 of 2

CERTIFICATE OF MAILING UNDER 37 CFR 1 10

I hereby certify that this correspondence is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1 10 on the date indicated below and is addressed to the Assistant Commissioner of Patents, Box PCT, Washington, D.C. 20231, on December 6, 2001.

(Signature of person mailing correspondence)

EV001613680US

"Express Mail" label number

Case No. 3142.2.2.1

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US)

Applicant:	Michael MCNEELY)
Int'l App. No.	PCT/US00/40156)
Int'l Filing Date:	8 June 2000)
Priority Date:	8 June 1999	,
Γitle:	LASER ABLATION OF DOPED FLUOROCARBON MATERIALS AND APPLICATIONS THEREOF	,

Preliminary Amendment

Box PCT

ď.

Assistant Commissioner for Patents Washington, D. C. 20231

Attn: DO/EO/US

Sir:

This paper is being filed concurrently with a Transmittal Letter to the United States Designated/Elected Office (DO/EO/US) Concerning a Filing under 35 U.S.C. § 371. Please enter the following amendments before beginning national examination procedures:

IN THE ABSTRACT OF THE DISCLOSURE:

The Applicant submits the following abstract on a separate sheet:

-- A method for laser ablation of doped fluorocarbon materials, such as fluorocarbon resins, and article fabrication applications using the laser ablation are disclosed. More specifically, a UV absorbing additive, such as carbon

black, is compounded with a fluorocarbon resin which is then subjected to laser ablation. The present invention is particularly useful for bulk structure fabrication, for example microstructure microfabrication.--

This "Abstract of the Disclosure" was taken from the Abstract published with the corresponding PCT patent application.

IN THE CLAIMS:

Please add new 27-30 claims as follows:

- 27. An article containing geometrical physical structures on or in a material prepared according to the method of claim 1.
- 28. An article containing geometrical physical structures on or in a material prepared according to the method of claim 8.
- 29. An article containing microstructures prepared according to the method of claim 16.
 - 30. A microfluidic structure prepared according to the method of claim 23.

Remarks

New claims 27-30 have been added. An Abstract of the Disclosure is also submitted.

Respectfully submitted,

Evan R. Witt Reg. No. 32,512

Date: December 6, 2001

MADSON & METCALF Gateway Tower West 15 West South Temple, Suite 900 Salt Lake City, Utah 84101 Telephone: 801/537-1700

c.\pct\3142 2.2.1.pre

ABSTRACT OF THE DISCLOSURE

A method for laser ablation of doped fluorocarbon materials, such as fluorocarbon resins, and article fabrication applications using the laser ablation are disclosed. More specifically, a UV absorbing additive, such as carbon black, is compounded with a fluorocarbon resin which is then subjected to laser ablation. The present invention is particularly useful for bulk structure fabrication, for example microstructure microfabrication.

5

WO 00/74890

5

10

15

20

25

30

PTO/PCT Rec'd 0 6 DEC 2001 10/009674 PCT/US00/40156

LASER ABLATION OF DOPED FLUOROCARBON MATERIALS AND APPLICATIONS THEREOF

BACKGROUND OF THE INVENTION

The present invention is directed to a method for laser ablation of fluorocarbon materials, such as fluorocarbon resins, and to applications for laser ablating such fluorocarbons. The present invention is particularly useful for bulk structure fabrication, e.g., microstructure microfabrication.

The publications and other materials used herein to illuminate the background of the invention, and in particular cases, to provide additional details respecting the practice, are incorporated by reference, and for convenience are numerically referenced in the following text and respectively grouped in the appended bibliography.

Fluorine resins have excellent heat resistance, chemical resistance and electrical characteristics that are rarely obtained from other synthetic resins. Characteristics of fluorocarbon resins can be modified by the inclusion of dopants. For example, U.S. Patent No. 4,405,544 describes the use of carbon black in Teflon to improve thermal conductance and electrical conductance for use as an electrode. Fluorocarbon polymer-pigment coating compositions have been stabilized against discoloration by doping with a metal oxide or hydroxide to improve color stability (U.S. Patent No. 4,150,008).

However, because fluorocarbons have an inactive surface, they have poor receptivity to adhesives, coatings or inks and are thus difficult to combine with other materials. It has also been difficult to surface or deep etch these resins. Several techniques for etching fluorocarbons have been developed, and these include ion beam etching (Garner et al., 1982), thermally assisted ion beam etching (Berenschot et al., 1996) and alkali metal vapor etching (U.S. Patent No. 4,855,018).

An additional technique that has been developed for modifying fluorocarbons is laser ablation. For example, vacuum assisted laser ablation using 4th harmonic (266mn) ND-YAG has been described for redeposition applications, such as coating another surface (Blanchet, 1993). Excimer laser ablation of doped Teflon AF films has been described in which the dopant was tris(perfluoroalkyl)triazine (Hiraoka et al., 1990). However, the method did not work with other thermally processed fluorocarbons. Micromachining of PTFE using radiation generated by a synchrotron (wavelengths: 0.1 nm-180 nm, usually 160 nm) in a vacuum is described in U.S. Patent No. 5,730,924. A similar process is described in U.S. Patent No. 5,555,549 for surface modification of fluoropolymers in general. Laser

ablation for micromachining of PTFE has also been described using either vacuum ultraviolet lasers whose wavelengths were 160 nm or 157 nm or ultrashort lasers (Kuper et al., 1989); Wada et al., 1993). PTFE resin material containing metal oxide dopants was marked using a laser (U.S. Patent No. 5,501,827). Surface modification of fluorine resin containing a dopant, such as other fluorocarbons, metal oxides, and carbon family elements, with laser light has been described in U.S. Patent No. 5,320,789.

High fluence UV lasers have become popular as tools for microfabrication. Their precise control of focused energy has been shown to remove small amounts of material on a substrate that absorbs UV light. The method of removal is photoablation, where atomic and molecular bonds are torn apart when high energy photons are absorbed, causing illuminated material to disassociate from the bulk. A cloud of gaseous debris can be observed above the material as it is illuminated with the laser. This precise control of material removal can allow for the fabrication of complex micro geometries. Laser ablation is not suitable for the removal of large amounts of material, due to very long processing times. It is very different than IR laser processing that is solely a thermal process where material is melted or burned away, leaving a considerable amount of molten debris, and where the control of material removal is limited. Depending on the material some thermal effects may also take place at UV wavelengths.

Many fluorocarbons, such as polytetrafluoroethylene (PTFE or Teflon), and tetrafluoroethylene (TFE) copolymerized with fluorinated ethylenepropylene (FEP), perfluoralkoxy alkane (PFA), and trifluoromethyl difluorodioxolene (Teflon AF) are mostly transparent to UV light of wavelengths greater than 200 nm. This makes them unsuitable for laser ablation because not enough energy is absorbed to break atomic and molecular bonds, although they may reach a high enough temperature that they melt locally. Some of these materials have shown ablation responses in the 157 nm wavelength range, which can be generated using a fluorine-fluorine excimer laser. However this type of laser is not very suitable for industrial use due to the care required to maintain the system and to operate it frequently. More suitable wavelengths for material processing are 222 nm (KrCI), 248 nm (KrF), 308 nm (XECI) and 351 nm (XeF) for excimer lasers and 266 nm for a quadrupled Nd-YAG laser. These are more suitable due to the longer life of the system optics and the ability to process the material in an ambient atmosphere of air. Thus, there is a need to develop an industrially useful method for laser ablation of fluorocarbon resins, especially for bulk structure fabrication, e.g., microstructure microfabrication.

SUMMARY OF THE INVENTION

5

10

15

20

25

30

The present invention is directed to a method for laser ablation of fluorocarbon materials, such as fluorocarbon resins, and to applications for laser ablating such fluorocarbons. More specifically, a UV absorbing additive is compounded with a fluorocarbon resin, which is then subjected to laser ablation. The laser ablation in accordance with the present invention can be applied to all forms of fluorocarbon resin including, but not limited to, extruded, sintered, or otherwise formed articles, films, tubes or sheets. The laser ablation can be used to surface modify fluorocarbon resins and can also be used for surface or deep etching. The laser ablation of doped fluorocarbons in accordance with the present invention is useful for applications including, but not limited to, changing surface properties and bulk properties to elicit hydrophilic effects, change color, change electrical properties, create fluid channels and wells, and general micromachining of substrate.

DETAILED DESCRIPTION OF THE INVENTION

Surface modification is a science whose purpose is to alter the natural state of the surface of a material to give it a characteristic more suitable for a specific application. Surface modification techniques rarely involve altering the characteristics of material deeper than a few hundred atomic layers inside the material. Surface modification is used to physically roughen a material to improve the adhesion of another material that will be deposited on the modified surface. It is used to expose unbound atomic bonds to make them available for covalent attachment to molecules that are introduced onto the material surface. It is used to clean the material surface and remove loosely bound particles. It can also be used to mark a surface by depositing or removing manometer deep layers of material, or somehow roughening the surface to expose a visible contrast. It is typically thought of as only altering a material in two dimensions (just the surface, with no depth)

Bulk micromachining, on the other hand, is used to generate geometrical physical structures on or in a material. It involves the manipulation of a significant volume of material (relatively speaking) and results in structures that have measurable 3-dimensional cross-sectional profiles. Examples of bulk micromachining are the fabrication of physical barriers to impede the flow of electrons or molecules (fluids), generation of vias to allow electrical connection between layers in a composite material, and mechanical fluid channels, micro gears, or cantilevers.

The present invention is directed to a method for laser ablation of fluorocarbon materials, such as fluorocarbon resins, and to applications for laser ablating such fluorocarbons. More specifically, a UV absorbing additive is compounded with a fluorocarbon resin, which is then subjected to laser ablation. Carbon black is a presently preferred UV absorbing additive. The present invention is particularly useful for bulk structure fabrication, e.g., microstructure microfabrication, which results from the use of dopants and high laser fluence.

5

10

15

20

25

30

The terms "fluorocarbon," "fluoroplastic," "fluoropolymer," "fluorocarbon resin," or "fluorine resin" as used herein means an organic polymeric material containing fluorine atoms, including, but non-limited to, poly(tetrafluoroethylene) (PTFE), poly(tetrafluoroethylene-co-perfluoroalkoxy-ethylene) (PFA), poly(tetrafluoroethylene-co-hexafluoropropylene) (FEP), poly(tetrafluoroethylene-co-hexafluoropropylene-co-perfluoroalkoxyethylene) (EPE), poly(tetrafluoroethylene-co-ethylene) (ETFE), poly(chlorotrifluoroethylene) (PCTFE), poly(chlorotrifluoroethylene-co-ethylene,) (ECTFE), poly(vinylidene fluoride) (PVDF), poly(vinyl fluoride) (PVF) and mixtures comprising two or more of these resins in arbitrary ratios.

The term carbon black is well known in the art. There are many types of carbon black that are distinguished by the method of manufacture, particle size, aggregate size, surface area, color, pH, and impurity content. Carbon black may also be known as graphite, graphite powder, or just carbon, and it includes carbon fiber and graphite fiber.

To facilitate ablation of fluorocarbon materials a UV absorbing additive is compounded with the fluorocarbon. While not being bound by any theory of operation, it is believed that the mechanism of ablation has changed from pure photoablation, to facilitated photoablation, where the UV absorbing material ablates, as one would expect, but it also removes some of the partially molten host material along with it. As a result of this phenomenon, the present invention is particularly well suited for bulk ablation, i.e., bulk structure fabrication.

The UV absorbing additive may be a metal oxide, organic dopant or carbon black. Known and novel UV absorbing additives may be used. Examples of some possible UV absorbing additives include Green 50, a compound that contains a mixture of cobalt, titanium, nickel and zinc oxides; Tinuvin® 328, an ultraviolet light absorber for plastics and coatings sold by Ciba-Geigy; Tinuvin® 770, an ultraviolet light absorber for plastics and coatings sold by Ciba-Geigy; and carbon black. There are many different carbon black

materials. Having tested several different types of carbon black, all appeared to work, to one degree or another, in accordance with the present invention.

5

10

15

20

25

30

The additive which is presently preferred and which has primarily been investigated is carbon black. The carbon black does not chemically bond with the host plastic, but acts as an interdispersed impurity. The uniformity of dispersion is dependent on the size of the initial carbon particle and the degree of mixing of the additive with the host plastic. Even small amounts of carbon black change the normally milky colored fluorocarbons to black. The effectiveness of ablation varies depending on the percentage and quality of additive that is compounded with the host material, and the fluence of the laser itself. Small percentages of carbon, such as 0.5 wt. % or less, do not ablate the host material away, but rather, the carbon itself is ablated away, leaving the milky colored host material in place. Materials with higher percentages of additive, such as 10 wt. % or more, are so highly absorbing that the ablation rate drops significantly and only small amounts of material are removed per laser pulse. This allows for more precise control of material removal, and smoother surface finishes, at the expense of low ablation rates. Very high levels of compounding also may adversely affect the material properties of the fluorocarbon. If low fluence levels are used the effect is similar to low amounts of carbon being present, that is the carbon ablates away and leaves uncolored host material behind.

The method of the present invention comprises irradiating laser light on or penetrating into a fluorocarbon resin containing a UV absorbing material. Laser ablation may be performed after molding, extruding, sintering or otherwise forming articles, films, tubes, sheets and the like.

The UV absorbing material is preferably used in an amount from about 0.1 wt. % to about 25 wt. %, preferably from about 0.5 to 15 wt. %, more preferably from about 1 to 10 wt. %, and most preferably about 4 to 6 wt. %. The amount of UV absorbing material used is dependent on the final application as described further herein. Typically, from about 0.1 to 0.5 wt. % carbon black is used in applications in which selective removal of carbon from a fluoroplastic is desired. Typically, higher percentages of carbon black, which results in lower ablation rates, are used for bulk laser ablation to achieve higher quality and better depth control. The preferred percentage of carbon black in this latter application is about 5 wt. %, typically from 4 to 6 wt. %.

The laser light used in the present invention is ultraviolet laser light having a wavelength from about 180 nm to about 400 nm, preferably from about 193 nm to about

355 nm, more preferably from about 248 nm to about 315 nm, and most preferably about 8 nm. A beam diameter of 50 μ m to 250 μ m can be used.

The fluence of the laser light used in the present invention is 0.1 J/cm²/pulse or higher, preferably 0.5 J/cm²/pulse or higher, and more preferably 0.9 J/cm²/pulse or higher. The laser fluence used is dependent on the amount of UV absorbing material and the final application as described further herein. Typically a low fluence of about 0.1 J/cm²/pulse to about 1 J/cm²/pulse can be used for selective removal of dopant from a fluoroplastic. A higher fluence, typically from about 1 J/cm²/pulse to about 10 J/cm²/pulse can be used for bulk ablation. It is anticipated that higher fluence lasers will be developed in the future; therefore, the present invention is not limited to a maximum fluence.

5

10

15

20

25

30

A rep rate of from about 10 to about 100 hertz or higher, such as up to 300 or 500 hertz, is used. The rep rate of some laser systems can be up to 1000 hertz. The rep rate determines how fast the laser ablation occurs. The translational movement of the laser may be from about 0.1 mm/sec to about 2 mm/sec.

Laser light irradiation is usually carried out in normal atmosphere at room temperature. If desired, it may also be carried out under reduced pressure or in an oxygen atmosphere and/or under heating or cooling. The conditions of laser light irradiation vary depending on the kind of fluorocarbon resin to be treated, the amount of UV absorbing material utilized and the application for which laser ablation is being applied.

Carbon black is compounded with a fluorocarbon resin using conventional techniques well known to a skilled artisan. For example, fluorocarbon resin powder and carbon powder are dry blended by means of a mixing machine, e.g., a tumbling mixer or a Henschel mixer, and the mixed powder is molded in a mold under a pressure of from about 160 to 500 kg/cm² to obtain a preform. The preform is subjected to sinter molding to form a molded article by a free baking method in which the preform is sintered in a hot air heating furnace at a sintering temperature of from about 360° to 380°C, a hot molding method in which the preform is sintered in a mold, or a continuous molding method using a ram extruder. In another example, a heat-fusible fluorine resin, such as PFA, and carbon powder are dry blended in a mixing machine, e.g., a tumbling mixer or a Henschel mixer, and the mixture is pelletized by means of an extruder. The mixture may be kneaded by means of, for example, a roll mill or a Banbury mixer and pelletized by means of a sheet pelletizer. The resulting blend pellets are molded into a rod, tubing, or film by means of an injection molding apparatus or an extruder. Other known processes to obtain molded, extruded,

sintered, or otherwise formed articles, films, tubes, sheets and the like may also be used to prepare the material for laser ablation.

5

10

15

20

25

30

The present invention can be exemplified using FEP and carbon black. FEP (fluorinated ethylene propylene) is an injection moldable form of Teflon. In its natural state FEP is milky white in appearance and is fairly transparent to UV light. In order to improve the UV absorption of the material FEP was compounded, with a carbon black additive. The addition of carbon black allows the FEP to absorb more UV radiation so it can be etched using a UV ablation process. The compounded material is coal black, even with very small percentages of carbon loading. The carbon black does not chemically bond with the host plastic, but acts as an interdispersed impurity. The uniformity of dispersion is dependent on the size of the initial carbon particles and the degree of mixing of the additive with the host plastic.

Laser ablation is performed by focusing a UV laser onto the plastic surface. The atomic and molecular bonds within the substrate absorb the laser energy and are excited to breakage. A cloud of gaseous debris is observed above the material as it is illuminated with the laser. This debris can be easily blown or sucked away. This mechanism differs from thermal ablation mechanism, such as with an IR laser, where the material becomes molten and splatters away from the incoming beam. Depending on the material some thermal ablation may take place at UV wavelengths. This thermal ablation is similar to what happens to FEP when no additive is present. Enough energy is absorbed to melt the material, but not enough to ablate it.

With the addition of the carbon black, the mechanism of ablation was assumed to be a combination of both thermal and photo absorption means. The carbon readily absorbs UV light, and as it is ablated it may remove some surrounding molten host material with it.

Carbon black is a common additive in plastics and is used primarily as a pigment, a UV absorber, a reinforcement filler, and as an electrical conductivity enhancer. The effectiveness of carbon black in achieving these desired results depends on the grade of the additive that is used, the percentage of loading, and its quality of dispersion within the host material. A process that selectively removes carbon from a host material in a highly controlled way could be used to control all of these qualities.

There are numerous potential applications of the ability to selectively leach out carbon black from a host material including, but not limited to, the applications described herein. The laser ablation process of the present invention includes the use of molded,

extended, sintered, or otherwise formed articles, films, tubes, sheet, and the like. The present method is used not for surface modification only, but for surface or deep etching, and the applications include changing surface properties and bulk properties to elicit hydrophilic effects, change color, change electrical properties, create fluid channels and wells, and general micromachining of substrate. The present invention is particularly useful for bulk structure fabrication, e.g., microstructure microfabrication.

5

10

15

20

25

30

The results of this work demonstrate that fluorocarbon materials, when compounded with UV absorbing additives, can be made processable by laser ablation, especially for bulk micromachining. In addition, the effect and efficiency of ablation can be tuned by adjusting both the percentage of additive in the material and the fluence of the laser beam used to ablate the material.

This process can be used to ablate holes and one, two and three-dimensional structures in bulk fluorocarbon plastics, films, coatings and tubing. Due to the chemical inertness and low surface energy properties of the fluorocarbons, the ability to easily process and form structures in this material has significant benefit. For example, microchannels and wells can be easily etched for microfluidic applications and small holes can be drilled into fluorocarbon tubing to allow non-aqueous phases to be selectively removed.

This process can be used to change the electrical conductivity of the host material. Depending on the percentage of carbon loading a plastic's electrical conductivity can range from that of an insulator, to a semi-conductor, to a conductor. It is conceivable that electrical circuit elements and traces could be fabricated in carbon-loaded fluorocarbons.

Changing the color of a material from black to white would be a straightforward process. It is irreversible and could be used as a visible pattern generation mechanism. This could be done for artistic purposes, or for technical marking where high precision is required. High precision patterns used to test optical elements are an example. Permanent bar-code patterns within a plastic part could also be fabricated. Some optical storage media are also based on variations of optical patterns in a material. It is also possible that a magnetic pattern may result by selectively removing the carbon. Magnetic effects of carbon loaded vs. native material are unknown at this time.

Selectively changing the mechanical properties of a material is also useful. It would be similar to making a composite structure, but with using only one material. This could allow a material to be bent more easily in a particular region, have a controlled breakage

findings were unexpected in view of prior art suggestions that laser ablation of doped fluoroplastics is only good for surface effects or film removal, i.e., either no penetration into bulk or no control of depth/quality of ablation.

The present invention is described by reference to the following Examples, which are offer by way of illustration and are not intended to limit the invention in any manner. Standard techniques well known in the art or the techniques specifically described below were utilized.

EXAMPLE 1

10

15

20

25

30

5

Laser Ablation of Fluorocarbon Resins

Various fluorocarbons resins were initially tested, including doped and undoped FEP, PFA, and PTFE. Doped samples were primarily FEP compounded with organic, metal oxide, and carbon black additives. The conditions of laser irradiation were as follows: beam diameter or 125 µm or 280 µm, fluence of 1-10 J/cm²/pulse, rep rate of 100 hertz, and translational movement of the laser of 0.1-2 mm/sec. The results of these initial studies confirmed lack of precision with metal oxides and organic dopants (which were suggested by the prior art as for surface modification applications). However, some control over depth/quality of laser ablation was seen with carbon black dopants at the high fluence tested. On the basis of these initial studies, further studies were conducted with carbon doped fluorocarbon resins.

EXAMPLE 2

Laser Ablation of Carbon Loaded FEP

While attempting to ablate carbon loaded FEP using a KrF laser operating at 248 nm, an interesting phenomenon was noticed. When the percentage of carbon black additive is low (approximately less than 0.5 wt. %) there is not enough carbon present in the material to effectively remove the host plastic. The carbon itself is removed from the material, but little or no host material is removed. The result is a selective removal of carbon that turns the material from its black color to its natural milky white appearance. If the laser is allowed to dwell, the depth of this removal increases, but thermal effects begin to distort the host material as well, causing it to melt and bubble. If the laser pulses once or only a few times in one place it appears as though the material is being 'bleached' due to the change in color. For this experiment, the laser energy was approximately 10 mJ and was operating at

a fluence of approximately 10 J/cm² at a rep rate of 100 Hz. The pulse width of the KrF laser is approximately 7-10 ns.

FEP of 5 different carbon loadings were ablated. The conditions of laser irradiation were as follows: beam diameter of 165 μm or 200 μm, fluence of 1-10 J/cm²/pulse, rep rate of 100 hertz and translational movement of the laser of 0.1-2 mm/sec. The percentages of loading were 0.01 wt. %, 0.5 wt. %, 1 wt. %, 5 wt. %, and 10 wt. %. In addition, PFA (another Teflon derivative) of 5 wt. % carbon loading was ablated. The bleaching effect was only observed on the 0.01 wt. % and 0.5 wt. % loaded material. The higher percentage material ablated without an obvious color change.

The bleaching was noticed because of the selective removal of carbon black from FEP. This effect is seen in other fluorocarbon polymers in which the UV absorbing material is miscible in the host material and in which there is a difference in the ablation rate of the host material and the additive.

15

20

25

10

EXAMPLE 3

Further Laser Ablation Studies

In further analysis of the laser ablation of carbon loaded fluorocarbons a second excimer laser was used. This laser operated at 248 nm, but had a shorter pulse width, approximately 3-4 ns. Table 1 shows approximate values of ablation depth per pulse for this KrF laser with an energy of approximately 1mJ per pulse and a beam diameter of approximately 160µm (after a demagnification of 10x from the output of the laser), for fluorocarbons with different percentages of carbon black additive. The carbon black additive was Regal 660 available from the Cabot Corporation Special Blacks Division. The lower ablation rates associated with higher percentages of carbon give greater depth control, however the speed of material removal is reduced and very high carbon loading can adversely affect the mechanical properties of the plastic. The quality of low carbon percentage ablation was very poor, leaving large amounts of bleached plastic "pillars" at the bottom of the resulting depressions.

CLAIMS:

20

 A method for bulk laser ablation of a fluorocarbon resin which comprises irradiating laser light onto or penetrating into a fluorocarbon resin containing a UV absorbing material.

- 5 2. The method of claim 1, wherein the UV absorbing material is present in the fluorocarbon resin in an amount from about 0.1 wt. % to about 25 wt. %.
 - 3. The method of claim 1, wherein the UV absorbing material is present in the fluorocarbon resin in an amount from about 0.5 wt. % to about 15 wt. %.
 - 4. The method of claim 1, wherein the UV absorbing material is carbon black.
- The method of claim 1, wherein the wavelength of laser light is from about 180 nm to about 400 nm.
 - 6. The method of claim 1, wherein the fluence of laser light is from about 0.1 J/cm²/pulse to about 1 J/cm²/pulse or higher.
- 7. The method of claim 1, wherein the fluence of laser light is from about 1 J/cm²/pulse to about 10 J/cm²/pulse.
 - 8. A method for bulk laser ablation of a fluorocarbon resin which comprises irradiating laser light onto or penetrating into a fluorocarbon resin containing a UV absorbing material, said UV absorbing material present in an amount of from about 0.1 wt. % to about 25 wt. %, the wavelength of the laser light is from about 180 nm to about 400 nm, the fluence of the laser light is greater than 0.5 J/cm²/pulse.
 - 9. The method of claim 8, wherein the dopant is present in an amount from about 0.5 wt. % to about 15 wt. %.
 - 10. The method of claim 8, wherein the dopant is present in an amount from about 1 to about 10 wt. %.
- 25 11. The method of claim 9, wherein the dopant is present in an amount of about 4 to 6 wt. %.
 - 12. The method of claim 8, wherein the dopant is carbon black.
 - 13. The method of claim 8, wherein the wavelength of the laser light is from about 193 nm to about 355 mn.
- 30 14. The method of claim 8, wherein the wavelength of the laser light is from about 248 nm to about 315 mn.

15. The method of claim 8, wherein the translational movement of the laser is from about 0.1 mm/sec to about 2 mm/sec.

- 16. A method of bulk microstructure microfabrication of a substrate comprising the steps:
- obtaining a fluorocarbon resin substrate containing a UV absorbing material, said UV absorbing material present in an amount of from about 0.1 wt. % to about 25 wt. %; and

irradiating laser light onto or penetrating into the fluorocarbon resin, the wavelength of the laser light being from about 180 nm to about 400 nm, the fluence of the laser light being greater than 1 J/cm²/pulse.

17. The method of claim 16, wherein the UV absorbing material is carbon black, a metal oxide, or a UV absorbing organic dopant.

10

20

25

30

- 18. The method of claim 16, wherein the UV absorbing material is carbon black.
- 19. The method of claim 16, wherein the UV absorbing material is present in the fluorocarbon resin in an amount from about 0.5 wt. % to about 15 wt. %.
 - 20. The method of claim 16, wherein the UV absorbing material is present in the fluorocarbon resin in an amount from about 1 wt. % to about 10 wt. %.
 - 21. The method of claim 16, wherein fluorocarbon resin is irradiated with the laser light of sufficient duration and intensity to fabricate microchannels and/or wells in the fluorocarbon resin substrate.
 - 22. A method of bleaching a substrate comprising the steps:
 obtaining a fluorocarbon resin substrate containing carbon black in an
 amount of from about 0.01 wt. % and 1 wt. %; and

irradiating laser light onto or penetrating into the fluorocarbon resin.

23. A method of microfabricating microfluidic structures in fluorocarbon materials comprising the steps:

obtaining a fluorocarbon resin substrate containing a UV absorbing material, said UV absorbing material present in an amount allowing for adequate depth control of material removal during the laser ablation process;

irradiating laser light onto or penetrating into the fluorocarbon resin, the wavelength of laser light being from about 193 nm to about 355 nm; and

translating the substrate or the laser beam relative to each other to generate microfluidic structures of the desired dimensions.

24. The method of claim 23 where the fluence of the laser light is greater than about 0.1 J/cm²/pulse.

25. The method of claim 23 where the fluence of the laser light is greater than about 1 J/cm²/pulse.

5

26. The method of claim 23, wherein the UV absorbing material is present in the fluorocarbon resin in an amount from about 0.5 wt. % to about 15 wt. %.

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date 14 December 2000 (14.12.2000)

(10) International Publication Number

(51) International Patent Classification7:

WO 00/74890 A1

- (21) International Application Number: PCT/US00/40156
- (22) International Filing Date:

8 June 2000 (08.06.2000)

(25) Filing Language:

English

B23K 26/00

(26) Publication Language:

English

(30) Priority Data: 60/138,091

8 June 1999 (08.06.1999) US

- (71) Applicants (for all designated States except US): MYR-IAD GENETICS, INC. [US/US]; 320 West Wakara Way, Salt Lake City, UT 84108 (US). BIOMICRO SYSTEMS. INC. [US/US]; 320 Wakara Way, Salt Lake City, UT 84108 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): MCNEELY, Michael [US/US]; 49 South 800 East #21, Salt Lake City. UT 84102 (US). OLIPHANT, Arnold [US/US]; 1563 West Erda Way, Erda, UT 84074 (US).

- Agent: MADSON & METCALF; Evan R. Witt, Suite 900, 15 West South Temple, Salt Lake City, UT 84101 (US).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH. GM. KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

With international search report.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: LASER ABLATION OF DOPED FLUOROCARBON MATERIALS AND APPLICATIONS THEREOF

(57) Abstract: The present invention is directed to a method for laser ablation of fluorocarbon materials, such as fluorocarbon resins, and to applications for laser ablating such fluorocarbons. More specifically, a UV adsorbing additive, such as carbon black, is compounded with a fluorocarbon resin which is then subjected to laser ablation. The present invention is particularly useful for bulk structure fabrication, e.g., microstructure microfabrication.

3142.2.2.1

Michael McNeely

Please type a plus sign (+) inside this box → +

DECLARATION FOR

PTO/SB/01 (3-97)

Approved for use through 9/30/98 OMB 0651-0032
Patent and Trademark Office, U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

Attorney Docket Number

First Named Inventor

UTILITY OR	DESIGN	COMPLETE IF KNOWN					
PATENT APPI	LICATION	App	olication Number				
			ng Date				
Declaration OR Declar Submitted Submi	ation tted after	Gro	oup Art Unit				
with Initial Initial Filing	Filing	Exa	ımıner Name				
As a below named inventor, I hereby	y declare that:						
My residence, post office address, a							
l believe I am an original, first and jo entitled:	int inventor of the subject m	atter w	vhich is claimed and for	which a patent is	sought on the invention		
LASER ABLATION O	F DOPED FLUOROCA			ID APPLICAT	IONS THEREOF		
the specification of which	(Titi	e of th	e Invention)				
is attached hereto							
OR was filed on (MM/DD/YYYY)	06/08/2000 a	s Unite	d States Application Nu	ımber or PCT Intei	rnational		
Application Number PCT/USOC	0/40156 and was amen	ded on	(MM/DD/YYYY)		(if applicable)		
I hereby state that I have reviewed amendment specifically referred to a		of the	above identified specif	ication, including 1	the claims, as amended by any		
I acknowledge the duty to disclose i		to pat	entability as defined in	Title 37 Code of F	ederal Regulations, § 1 56		
l hereby claim foreign priority benefi inventor's certificate, or § 365 (a) o America, listed below and have also PCT international application having	f any PCT international appli identified below, by checkin	cation t g the b	which designated at lea box, any foreign applicat	ist one country ot tion for patent or	her than the United States of		
Prior Foreign Application Number(s)	Country		Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached? Yes No		
60/138,091	United States	06/08/1999					
Additional foreign application	n numbers are listed on a sup	plemer	ntal priority data sheet f	PTO/SB/02B attac	hed hereto.		
I hereby claim the benefit under Title	e 35, United Stated Code §	119(e)	of any Untied States pr	ovisional applicati	on(s) listed below		
Application Number(s)	Filing D	ate (MN	M/DD/YYYY)	Additional provisional application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto			
			<u></u>				

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, D.C. 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO. Assistant Commissioner for Patents, Washington, D.C. 20231.

Please type a plus sign (+) inside this box → +

PTO/SB/01 (3-97)
Approved for use through 9/30/98 OMB 0651-0032
Patent and Trademark Office U S DEPARTMENT OF COMMERCE

Patent and Trademark Office U.S. DEPARTMENT OF COMM Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

DECLARATION — Utility or Design Patent Application

designating the prior United St duty to disclos	hereby claim the benefit under Title 35, United States Code § 120 of any United States application(s), or § 365(c) of any PCT International Application lesignating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the mirror United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code § 112, I acknowledge the luty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations § 1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.										
	U.S F	Parent Application or F Number	PCT Parent			Parent Filing Date Pa (MM/DD/YYYY)			Pare	ent Patent Number (If applicable)	
Additional	U.S or PC	CT international applica	tion numbers	are liste	d on a sur	plemental p	priority da	ata shee	t PTO/SB/02	2B atta	ched hereto.
As a named inventor, I hereby appoint the following registered practitioner(s) to Patent and Trademark Office connected therewith. OR OR					to prosecute this application and to transact all business in the						
	Nam	ne		istration umber			I	Name			Registration Number
Additional	registered	practitioner(s) named	on supplemen	ntal Regi	stered Pra	ctitioner Inf	ormation	sheet P	TO/SB/02C	attach	ed hereto
Direct all corr	esponder	nce to: 🗶 Customer N or Bar Code La		.21	552		OR	Co	rresponden	ce ado	tress below
Name	Evan	R. Witt									
Address								- 			
Address							,	,	T		
City				•		State		ZIP			
Country			Telephone	<u></u>				Fax	L		
N	lame of l	nventor					<u> </u>	J A peti	tion has bee	n filed :	for this unsigned inventor
Given Name (fi	rst and mi	ddle (if anyl)				Family Name or Surname					
.Arnold—					Oliphant						
Inventor's Sign	ature	ah	<u></u>	50	4	/			4/2	/2000	
Residence; City		Erda		State	Ut	Country	US	41	Citizens	hip	US
Post Office Ad	dress	1563 West Erd	a Way								
City		Erda	State	UT	Zip	84074			Country	us	
Additional	Additional inventor are being named on supplemental Additional Inventor(s) sheet(s) PTO/SB/02A attached hereto										

[Page ____ of ____]

3142.2.2.1

COMPLETE IF KNOWN

Michael McNeely

Please type a plus sign (+) inside this box → +

DECLARATION FOR

UTILITY OR DESIGN

PATENT APPLICATION

PTO/SB/01 (3-97)
Approved for use through 9/30/98 OMB 0651-0032
Patent and Trademark Office. U S. DEPARTMENT OF COMMERCE

Patent and Trademark Office. U S. DEPARTMENT OF COMMERC Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number

Attorney Docket Number

First Named Inventor

Application Number

Filing Date

■ Declaration OR ■ Declar	ration								
Submitted Subm	itted after	Group Art Unit							
with Initial Initial Filing	Filing	Examiner Name							
As a below named inventor, I hereby declare that:									
My residence, post office address, ar	nd citizenship are as stated belo	w next to my name.							
I believe I am an original, first and join	nt inventor of the subject matter	which is claimed and for w	hich a patent is soug	ht on the invention entitled:					
LASER ABLATION OF			AND APPLICA	ATIONS THEREOF					
the specification of which	(Title	of the Invention)		_					
is attached hereto									
OR was filed on (MM/DD/YYYY)	06/08/2000 as	Jnited States Application N	Jumber or PCT Intern	ational					
Application Number PCT/USO		d on (MM/DD/YYYY)	Tambér et l'Ol main	(if applicable)					
	·· ··								
I hereby state that I have reviewed ar amendment specifically referred to at		e above identified specifica	ation, including the ci	aims, as amended by any					
I acknowledge the duty to disclose inf	formation which is material to pa	tentability as defined in Tit	le 37 Code of Federa	l Regulations, § 1 56.					
I hereby claim foreign priority benefits inventor's certificate, or § 365 (a) of a listed below and have also identified be international application having a filing	my PCT international application below, by checking the box, any	which designated at least foreign application for pate	one country other that ent or inventor's certif	an the United States of America,					
Prior Foreign Application Number(s)	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached? Yes No					
06/08/1999									
Additional foreign application	numbers are listed on a suppler	nental priority data sheet P	TO/SB/02B attached	hereto.					
I hereby claim the benefit under Title 35, United Stated Code § 119(e) of any Untied States provisional application(s) listed below:									
Application Number(s)	Filing Date	e (MM/DD/YYYY)	are listed	provisional application numbers on a supplemental priority data D/SB/02B attached hereto					

[Page ____ of ___]

Burden Hour Statement This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, D.C. 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO. Assistant Commissioner for Patents, Washington, D.C. 20231.

Please type a plus sign (+) inside this box → +

PTO/SB/01 (3-97)
e a plus sign (+) inside this box

Approved for use through 9/30/98 OMB 0651-0032
Patent and Trademark Office U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number

DECLARATION — Utility or Design Patent Application

United States of International apmaterial to pate	I hereby claim the benefit under Title 35, United States Code § 120 of any United States application(s), or § 365(c) of any PCT International Application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code § 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations § 1 56 which became available between the filing date of the prior application and the national or PCT international filing date of this application										
U.S Parent Application or PCT Parent Number						Parent Filing Date (MM/DD/YYYY)				Par	ent Patent Number (if applicable)
Additional U	S or PC	Γ international application	numbers are l	isted on	a supplem	ental priority	data shee	et PTO/S	B/02B attach	ed her	eto
OR						secute this application and to transact all business in the 21552 Place Customer Number Bar Code Label Here ner(s) name/registration number listed below					ustomer Number
	Nan	ne		gistration umber				Name			Registration Number
Additional re	gistered p	practitioner(s) named on s	supplemental R	Registere	d Practition	ner Informatio	n sheet F	PTO/SB/0	2C attached	hereto)
Direct all corre	sponden	ce to: 🛛 Customer Nu or Bar Code La	mber bel	215	52	OR Correspondence address below					
Name	Evan	R. Witt									
Address		······································							•		
Address											
City						State		ZiP			
Country			Telephone					Fax			
Name o	of Sole o	r First Inventor				• · · • · · · · · · · · · · · · · · · ·		A petiti	on has been	filed fo	or this unsigned inventor
Given Name (fir	st and mid	ddle [if any])				Family Name or Surname					
Michael . McNeely.											
Inventor's Signature Mulacome Notes				Date				3/28/01			
Residence: City Sandy				State	Ut	Country	US		Citizensi	nip	US
Post Office Add	ress	2159 East Powd	erkeg Driv	ट		U7	1				
City Sandy State UT Zip				Zıp	84093 Country US						
Additional in	Additional inventor are being named on supplemental Additional Inventor(s) sheet(s) PTO/SB/02A attached hereto.										

[Page ____ of ___]